

ADVANCE PAINTS

CORROSION PROTECTION PROFESSIONALS

CIN: U24110MH1941PTC003381

Advolite 1141 BT

Anti-corrosive Bitumen Coating

GENERAL DESCRIPTION	Single pack anti-corrosive coating based on bitumen fortified with special extenders and aluminium. It has good water & moisture repellant properties.
RECOMMENDED USE	For structural steel, and other metal surfaces in marine environment for both submerged and above water areas.

PHYSICAL DATA	
Colour	Brown
Finish	Egg-shell to matt
Volume Solids (by ASTM D 2697)	40 ±2%
Recommended Dry Film Thickness	50μ per coat
Theoretical Spreading Rate	8 m² per litre @ 50μ DFT
Flash Point	>30°C

Temperature	Touch Dry	Hard Dry	Overcoating	Interval
			Minimum	Maximum
15°C	3 hours	12 hours	12 hours	Indefinite
25°C	2 hours	10 hours	10 hours	Indefinite
35°C	1½ hours	8 hours	8 hours	Indefinite



ADVANCE PAINTS

CORROSION PROTECTION PROFESSIONALS

CIN: U24110MH1941PTC003381

Thinner Recommended	Thinner for Advolite
Shelf Life	12 months

SURFACE PREPARATION	Remove oil, grease etc with a detergent wash. Remove Salt and other contaminants by high pressure fresh water hosing. Remove all rust and loose materials by abrasive blasting or mechanical cleaning. Dust off residues. For best results remove all loose rust by wire brushing and chipping.
------------------------	---

APPLICATION DATA Method Pressure ((Atm) Nozzle Orifice Thinner Volume Brushing - - Thinner for Advolite 3 – 5%



ADVANCE PAINTS

CORROSION PROTECTION PROFESSIONALS

CIN: U24110MH1941PTC003381

 In case of contamination, rinse with fresh running water and seek medical help at once 3. Provide sufficient ventilation when working with solvent based coatings in confine spaces and stagnant air. Follow Local and National Safety Rules. NOTE Thinner consumption and loss factor in practical coverage of paint depends upon the site condition. 	Air Spray Conventional		4-5	0.021 - 0.031	Thinner for Advolite	5 - 10%	
2. In case of contamination, rinse with fresh running water and seek medical help at once 3. Provide sufficient ventilation when working with solvent based coatings in confine spaces and stagnant air. 4. Follow Local and National Safety Rules. 1. Thinner consumption and loss factor in practical coverage of paint depends upon the site condition. 2. Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use glower and goggles to protect against direct contact of paint with skin and eyes.	Airless Spray		4 - 5	0.021 - 0.031	Thinner for Advolite	0 - 3%	
 In case of contamination, rinse with fresh running water and seek medical help at once 3. Provide sufficient ventilation when working with solvent based coatings in confine spaces and stagnant air. Follow Local and National Safety Rules. 1. Thinner consumption and loss factor in practical coverage of paint depends upon the site condition. Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use glow and goggles to protect against direct contact of paint with skin and eyes. 							
site condition. 2. Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use glove and goggles to protect against direct contact of paint with skin and eyes.	 In case of contamination, rinse with fresh running water and seek medical help at o Provide sufficient ventilation when working with solvent based coatings in con spaces and stagnant air. 					-	
4. Information given here is in good faith without warranty.			site condition. Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use gloves and goggles to protect against direct contact of paint with skin and eyes. This cancels all previous information sheets for this Product.				

The information given above is to the best of our knowledge and laboratory results. As we do not have control over the quality of the substrate, application conditions, and the skill of the applicator, we do not take any responsibility for the loss or damage caused due to wrong use of the product. We recommend the user to test the product for its suitability.

Contact: Advance Paints Pvt. Ltd.

Advance House, Plot 'A', Ark Industrial Compound, Makwana Road, Off Andheri Kurla Road, Marol Naka, Andheri East, Mumbai: 400 059.

Email: metashield@advancepaints.com Contact No. (022) 28590162, 63, 64

MP/1b

AP/104/O&G/Nov23

ADVANCE PAINTS PVT. LTD.