

# **ADVANCE PAINTS**

**CORROSION PROTECTION PROFESSIONALS** 

CIN: U24110MH1941PTC003381

### Advotherm HR 3125

Heat Resistant - 250°C Oleoresinous Based Coating

GENERAL DESCRIPTION	A Two pack coating specially formulated on Oleo Resin and pigmented with Aluminium flakes to protect steel surfaces operating at temperatures up to 250°C.
RECOMMENDED USE	On Stacks, Boiler casings, Exhaust pipes, hot Pipelines, pumps & manifolds, Process vessels and equipments which reach temperature up to 250 °C.

**PHYSICAL DATA** Aluminium Colour Finish **Metallic Lustrous** 0.90 ±0.05 Specific Gravity Mixing Ratio (By Weight) 85:15 Volume Solids (by ASTM D 2697) 31 ±1% Viscosity 30 seconds @ 27 ± 2°C **Recommended Dry Film Thickness** 20 - 25<sub>µ</sub> 12 m² per litre @ 25µ DFT **Theoretical Spreading Rate** 

Flash Point

Temperature	Touch Dry	Hard Dry*	Overcoating Interval		
	·		Minimum	Maximum	
15°C	8 hours	18 hours	24 hours	Indefinite	
25°C	4 hours	14 hours	16 hours	Indefinite	
35°C	3 hours	12 hours	12 hours	Indefinite	

>26°C

Thinner Recommended Shelf Life	

# SURFACE PREPARATION New Steel: Blast cleaning to SA 2½. An average surface profile of 10 to15μ is acceptable but it should not exceed 20μ. Maintenance: Remove oil, grease, Salt, loose paint, rust or any other contaminants. In contaminated environment hose down with fresh water & allow to dry.

#### ADVANCE PAINTS PVT. LTD.

Sewri Factory: 2nd. Fosbery Road, Near Hindustan Lever Ltd. Sewri (E), Mumbai 400 015, India
Tele Fax: +91 22 2374 3304/05 • M: +91 90225 38579 • advancsew@advancepaints.com • www.advancepaints.com



## **ADVANCE PAINTS**

## CORROSION PROTECTION PROFESSIONALS

CIN: U24110MH1941PTC003381

Method  Brushing  Air Spray Conventional		Pressure ((Atm)	Nozzle Orifice 0.021 - 0.031	Thinner Thinner for Advotherm Thinner for Advotherm	*Thinner Volume - -		
						4 - 5	
		SAFETY PRECAUTIONS				<ol> <li>Keep the material away from heat, spark, and direct flame.</li> <li>In case of contamination, rinse with fresh running water and seek medical help at once.</li> <li>Provide sufficient ventilation when working with solvent based coatings in confined space and stagnant air.</li> <li>Follow Local and National Safety Rules.</li> </ol>	
	ran San November	<ol> <li>Thinner consumption and loss factor in practical coverage of paint depends upon the sit condition.</li> <li>Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use gloves ar goggles to protect against direct contact of paint with skin and eyes.</li> <li>This cancels all previous information sheets for this Product.</li> <li>Information given here is in good faith without warranty.</li> </ol>					

The information given above is to the best of our knowledge and laboratory results. As we do not have control over the quality of the substrate, application conditions, and the skill of the applicator, we do not take any responsibility for the loss or damage caused due to wrong use of the product. We recommend the user to test the product for its suitability.

Contact: Advance Paints Pvt. Ltd.

Advance House, Plot 'A', Ark Industrial Compound, Makwana Road, Off Andheri Kurla Road, Marol Naka,

Andheri East, Mumbai: 400 059.

Email: metashield@advancepaints.com Contact No. (022) 28590162, 63, 64