

ADVOWASH 1211 (Etch Primer)

GENERAL DESCRIPTION

Two-pack phosphoric acid cured Etch Primer with excellent adhesion and flexibility. It complies IS : 5666-1970. Its excellent adhesion on aluminium and galvanized steel ensure the adhesion of Subsequent coating system.

RECOMMENDED USE

For Aluminium, Galvanised Iron, & Light Alloy surfaces to improve adhesion of subsequent coats. It can be used in conjunction with other primers.

PHYSICAL DATA

Colour	Yellowish Green
Finish	Matt
Volume Solids (by ASTM D 2697)	10 ± 2 %
Mixing Ratio (By Volume)	1 : 1
Recommended Dry Film Thickness	8 – 12 µm per coat
Wet Film Thickness	60 -80 µm per coat
Theoretical Spreading Rate	10.0 m ² per litre @ 20 µm DFT
Flash Point	>13 °C

DRYING TIME:

* Precaution: Do Not apply at DFT more than 12 µm as at higher DFT adhesion will be impaired.

Drying times are generally depend on air circulation, ambient temperature, film thickness and number of coats, and will be affected accordingly. The figures given in table below are indicative only.

ADVANCE PAINTS PVT. LTD.

TEMPERATURE		15°C	25°C	35°C
INDUCTION TIME		20 Minutes	15 Minutes	10 Minutes
TOUCH DRY		30 Minutes	25 Minutes	20 minutes
HARD DRY		8 hours	6 hours	4 hours
OVERCOATING INTERVAL	MINIMUM	4 hours	3 hours	2 hours
	MAXIMUM	24hours	24 hours	24 hours
POT LIFE		10 hours	8 hours	6 hours

THINNER RECOMMENDED	N/A
SHELF LIFE	12 months @ 25°C

LIMITATION	
POT LIFE	If viscosity of mixed paints reaches more than double of initial viscosity do not apply the mixed paint anymore
BLASTING OR APPLICATION	N/A

SURFACE PREPARATION	Accumulated dirt and solvent salts must be removed by brush followed by fresh water cleaning. Repeat the process still the surface is free from chloride & dry it. Oil and grease should be removed following SSPC-SPI solvent cleaning.
----------------------------	--

ABRASION BLAST CLEANING	N/A
--------------------------------	-----

MIXING METHOD	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Agitate Base (Part A) with pneumatic stirrer add slowly hardener (Part B) for 3-5 minutes till the mixture becomes homogeneous. Do not add thinner. Do not apply at >12 microns. Maximum adhesion is achieved at 8 – 10 micron.
----------------------	---

ADVANCE PAINTS PVT. LTD.

AIRLESS APPLICATION	N/A
CONVENTIONAL AIR SPRAY	Air Spray Gun (Pilot Type 59) Pressure: 2.5 – 3 kg/cm ² Tip size :1.2 – 1.8 mm
BRUSH APPLICATION	Can be applied by brush without thinning. Avoid runs or sags. Do not apply when humidity is very high (>95°C) or the ambient temperature is below 3°C of dew point..
STORAGE	The product must be store below 25°C and in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space, and away from source of heat and ignition. Containers must be kept tightly closed.
SAFETY PRECAUTIONS	Keep the material away from heat, spark, and direct flame. In case of contamination, rinse with fresh running water and seek medical help at once. Provide sufficient ventilation when working with solvent based coatings in confined spaces and stagnant air. Follow Local and National Safety Rules.
WORK STOPPAGE	Clean the hoses, gun or spray equipment with water immediate after application. Do not allow material to remain in the equipment system.

CLEAN UP	Clean all equipment thoroughly with water immediately after use. As part of good working practices, spray equipment should also be flushed periodically during the working day. The frequency of cleaning depends on factors such as the volume of material sprayed, ambient temperature, and the duration of any delays or downtime. Dispose of all surplus materials and empty containers responsibly, in compliance with applicable regional regulations and legislation.
NOTE	Thinner consumption and loss factor in practical coverage of paint depends upon the site condition. Avoid inhalation of solvent vapour or paint mist by using facial mask. Also use gloves and goggles to protect against direct contact of paint with skin and eyes. This cancels all previous information sheets for this Product. Information given here is in good faith without warranty.
DISCLAIMER	The information provided in this document is based on Advance Paints best knowledge, derived from laboratory testing and practical experience. As Advance Paints products are considered semi-finished goods, they are often used under conditions beyond the company's control. Therefore, Advance Paints can only guarantee the quality of the product itself and cannot assume responsibility for its performance under all circumstances. Minor variations in the product may occur to meet local requirements. Advance Paints reserves the right to amend the provided data without prior notice. Users should always consult Advance Paints for specific guidance on the suitability of this product for their particular needs and application practices.

Issue date: 1 August 2023

This data sheet is not exhaustive. For further information or additional details, please reach out to our Technical Service Team.

ADVANCE PAINTS PVT. LTD.